



BUILDING SERVICES & UTILITIES

Crane House,
Epsilon Terrace, West Road,
Ipswich, Suffolk IP3 9FJ
Tel: +44 (0)1473 277400
Fax: +44 (0)1473 277411
Web: www.cranesbu.com

Temperature, Celsius	Aluminium Bronze			Brass (a)			Copper			Copper-Nickel 90/10 alloys (b)			Gunmetal and Bronze (c)		
	20°	60°	100°	20°	60°	100°	20°	60°	100°	20°	60°	100°	20°	60°	100°
Phosphoric acid (20%)	R	R	R	X	X	X	R	R	R	R	R	X	X	X	X
Phosphoric acid (50%)	R	R	R	X	X	X	X	X	X	R	R	X	X	X	X
Phosphoric acid (95%)	R	R	R	X	X	X	X	X	X	R	X	X	X	X	X
Phosphorus chlorides	R(11)	R(11)	R(11)	X	X	X	X	X	X	R	X	X	X	X	X
Phosphorous pentoxide	No data	No data	No data	X	X	X	X	X	X	No data	No data	No data	X	X	X
Phthalic acid	R	R	R	No data	No data	No data	R	R	R	R	R	R	R	R	R
Picric acid	X	X	X	X	X	X	X	X	X	R	R	R	R	R	R
Pyridine	No data	No data	No data	X	X	X	X	X	X	No data	No data	No data	X	X	X
Salicyl aldehyde	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data	No data
Sea water	R	R	R	R(62)	R	R	R	R	R	R	R	R	R	R	R
Silicic acid	R	R	R	No data	No data	No data	R	R	R	X	X	X	No data	No data	No data
Silicone fluids	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Silver nitrate	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Sodium carbonate	R	R	R(4)	R	R	R	R	R	R	R	R	R	R	R	R
Sodium peroxide	X	X	X	X	X	X	X	X	X	R	X	X	X	X	X
Sodium silicate	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Sodium sulphide	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Stannic chloride	R(11)	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Starch	R	R	X	No data	No data	No data	R	R	R	R	R	R	R	R	R
Sugar soln, syrups, jams	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Sulphamic acid	No data	No data	No data	X	X	X	X	X	X	No data	No data	No data	X	X	X
Sulphates (Na, K, Mg, Ca)	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Sulphites	R	R	R	X	X	X	R	R	R	R	R	R	R	R	R
Sulphonic acids	No data	No data	No data	No data	No data	No data	X	X	X	No data	No data	No data	No data	No data	No data
Sulphur	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Sulphur dioxide, dry	R	R	R	R	R	R	R	R	R	R	R	X	R	R	R
Sulphur dioxide, wet	R	R	R	X	X	X	X	X	X	X	X	X	X	X	X
Sulphur dioxide, (96%)	R	R	R	X	X	X	R(20)	R(20)	X	R	R(20)	X	R(20)	R(20)	R(20)
Sulphur trioxide	R(11)b	R	R	R(11)	R	R	R(11)	R	R	R(11)	R	X	R(11)	R	R
Sulphuric acid (<50%)	R	R	R	X	X	X	R	R	R	R	X	X	X	X	X
Sulphuric acid (70%)	R	R(62)	X	X	X	X	X	X	X	R	X	X	X	X	X
Sulphuric acid (95%)	R(62)	X	X	X	X	X	X	X	X	R	X	X	X	X	X
Sulphuric acid, fuming	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Sulphur chlorides	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Tallow	R	R	R	No data	No data	No data	R	R	R	R	R	R	No data	No data	No data
Tannic acid (10%)	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Tartaric acid	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Trichlorethylene	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Urea (30%)	R	R	X	R	R	X	R	R	X	R	R	X	R	R	No data
Vinegar	R	R	R	X	X	X	X	X	X	R	R	R	X	X	X



Temperature, Celsius	Aluminium Bronze			Brass (a)			Copper			Copper-Nickel 90/10 alloys (b)			Gunmetal and Bronze (c)		
	20°	60°	100°	20°	60°	100°	20°	60°	100°	20°	60°	100°	20°	60°	100°
Water, distilled	R(53)	R	X	X	X	X	R(53)	R	X	R	R	R	R(53)	R	R
Water, soft	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Water, hard	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Wetting agents (to 5%)	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Yeast	No data	No data	No data	No data	No data	No data	R	R	R	No data	No data	No data	R	R	R
Zinc chloride	R	R	R	X	X	X	X	X	X	X	X	X	X	X	X

This document is intended as guidance only. The onus for determining correct dosing remains with the user.

Crane (and its related brands) manufacture hardware (valves, couplings, etc) for the Building Services industry and Utilities industries (including Gas and Water industries) however, we are not system designers or operators. The use of chemicals for system dosing must be determined by the user as all aspects of system variables (biocides, inhibitors, system medium, raw water condition (where used), existing micro-biological processes within the system, temperature, mechanical configuration, etc) must be established and considered, and the effect of the chemicals used (including compounds arising from chemical combinations) must also be established in order to accurately determine compatibility. Crane cannot make recommendations regarding chemical compatibility for the system, as a result of the above variables, which includes all components, substances and materials. Any comments from Crane regarding chemical compatibility shall relate solely to the Crane product and does not constitute a recommendation on compatibility for the wider system, resultant chemical compounds, components, substances or materials, in whole or in part.

Footnotes:

- (a) Brass: Some types of brass have less corrosion resistance than is shown on the chart, others have more, e.g. Aluminium brass
- (b) Copper-nickel alloys: Based on behaviour of Cu/Ni 90/10; 70/30 may be generally more resistant
- (c) Gunmetal: The data refer only to high tin gunmetals
- (2) Depending on the acid
- (4) Fair resistance
- (11) Anhydrous
- (20) Not aerated solutions
- (30) Depending on composition
- (36) Over 85%
- (53) In absence of dissolved O₂ and CO₂
- (60) May discolour liquid/ product
- (62) Depending on type
- (73) Not ammonium
- (82) Provided more than 70% copper
- (83) Water less than 150ppm
- (119) Pure solution
- (175) With stabiliser